


09/25/00
Jc715 U.S. PTO

U.S. PTO
09/25/00
Jc715 U.S. PTO

UTILITY PATENT APPLICATION TRANSMITTAL <small>new nonprovisional applications under 37 C.F.R. 1.53(b)</small>		Attorney Docket No. 1247-0849-6VF
First Inventor or Application Identifier	Jean-Paul DEBALME	
Title	PROCESS FOR MANUFACTURING A COMPOSITE TAPE FORMED FROM REINFORCING FIBRES AND FIBRES OF A THERMOPLASTIC ORGANIC MATERIAL	

APPLICATION ELEMENTS <small>See MPEP chapter 600 concerning utility patent application contents</small>		ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20231
1. <input checked="" type="checkbox"/> Fee Transmittal Form (e.g. PTO/SB/17) <small>(Submit an original and a duplicate for fee processing)</small>	ACCOMPANYING APPLICATION PARTS	
2. <input checked="" type="checkbox"/> Specification Total Pages 18	6. <input checked="" type="checkbox"/> Assignment Papers (cover sheet & document(s))	
3. <input checked="" type="checkbox"/> Formal Drawing(s) <small>(35 U.S.C. 113)</small> Total Sheets 3	7. <input type="checkbox"/> 37 C.F.R. §3.73(b) Statement <input type="checkbox"/> Power of Attorney <small>(when there is an assignee)</small>	
4. <input checked="" type="checkbox"/> Oath or Declaration Total Pages 4	8. <input type="checkbox"/> English Translation Document (if applicable)	
a. <input checked="" type="checkbox"/> Newly executed (original)	9. <input checked="" type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input checked="" type="checkbox"/> Copies of IDS Citations (2)	
b. <input type="checkbox"/> Copy from a prior application (37 C.F.R. §1.63(d)) <small>(for continuation/divisional with box 15 completed)</small>	10. <input checked="" type="checkbox"/> Preliminary Amendment	
i. <input type="checkbox"/> DELETION OF INVENTOR(S) <small>Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §1.63(d)(2) and 1.33(b).</small>	11. <input checked="" type="checkbox"/> White Advance Serial No. Postcard	
5. <input checked="" type="checkbox"/> Incorporation By Reference <small>The entire disclosure of the priority to French Patent Application No. 99/13067 filed on October 20, 1995, is considered to be part of the disclosure of the accompanying application and is hereby incorporated by reference therein.</small>	12. <input type="checkbox"/> Small Entity Statement(s) <input type="checkbox"/> Statement filed in prior application. Status still proper and desired.	
13. <input checked="" type="checkbox"/> Certified Copy of Priority Document (1) <small>(if foreign priority is claimed)</small>		
14. <input checked="" type="checkbox"/> Other: Request for Priority Statement of Relevancy		
15. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below: <input type="checkbox"/> Continuation <input type="checkbox"/> Divisional <input type="checkbox"/> Continuation-in-part (CIP) of prior application no.: Prior application information: Examiner: Group Art Unit:		
16. Amend the specification by inserting before the first line the sentence: <input type="checkbox"/> This application is a <input type="checkbox"/> Continuation <input type="checkbox"/> Division <input type="checkbox"/> Continuation-in-part (CIP) of application Serial No. Filed on <input type="checkbox"/> This application claims priority of provisional application Serial No. Filed		
17. CORRESPONDENCE ADDRESS  22850 (703) 413-3000 FACSIMILE: (703) 413-2220		

Name:	Gregory J. Maier	Registration No.:	25,599
Signature:	<i>Cr. Way</i>	Date:	8-14-2000
Name:	Christopher D. Ward	Registration No.:	41,367

Docket No. 1247-0849-6VF

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

INVENTOR(S) Jean-Paul DEBALME, et al.

SERIAL NO: New Application

FILING DATE: Herewith

FOR: PROCESS FOR MANUFACTURING A COMPOSITE TAPE FORMED FROM REINFORCING FIBRES...

FEE TRANSMITTAL

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

FOR	NUMBER FILED	NUMBER EXTRA	RATE	CALCULATIONS
TOTAL CLAIMS	19 - 20 =	0	× \$18 =	\$0.00
INDEPENDENT CLAIMS	1 - 3 =	0	× \$78 =	\$0.00
<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS (If applicable)			+ \$260 =	\$0.00
<input type="checkbox"/> LATE FILING OF DECLARATION			+ \$130 =	\$0.00
BASIC FEE				\$690.00
TOTAL OF ABOVE CALCULATIONS				\$690.00
<input type="checkbox"/> REDUCTION BY 50% FOR FILING BY SMALL ENTITY				\$0.00
<input type="checkbox"/> FILING IN NON-ENGLISH LANGUAGE			+ \$130 =	\$0.00
<input checked="" type="checkbox"/> RECORDATION OF ASSIGNMENT			+ \$40 =	\$40.00
TOTAL				\$730.00

- ☐ Please charge Deposit Account No. 15-0030 in the amount of _____ A duplicate copy of this sheet is enclosed.
- ☒ A check in the amount of **\$730.00** to cover the filing fee is enclosed.
- ☒ The Commissioner is hereby authorized to charge any additional fees which may be required for the papers being filed herewith and for which no check is enclosed herewith, or credit any overpayment to Deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.

Respectfully Submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.

Ch. Ward

Gregory J. Maier
Registration No. 25,599

Christopher D. Ward
Registration No. 41,367

Date: 9-14-2000



22850

Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 11/98)

GJM:CDW:brf

1247-0849-6VF

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

IN RE APPLICATION OF: :

Jean-Paul DEBALME, et al. :

SERIAL NO.: New Application :

FILED: Herewith :

FOR: PROCESS FOR :
MANUFACTURING A
COMPOSITE TAPE FORMED
FROM REINFORCING FIBRES
AND FIBRES OF A
THERMOPLASTIC ORGANIC
MATERIAL

PRELIMINARY AMENDMENT

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Prior to consideration of the above-identified application, please amend the
application as follows:

IN THE SPECIFICATION

Please amend the specification as follows:

Page 1, before line 1, insert

--TITLE OF THE INVENTION

PROCESS FOR MANUFACTURING A COMPOSITE TAPE FORMED
FROM REINFORCING FIBRES AND FIBRES OF A THERMOPLASTIC
ORGANIC MATERIAL

BACKGROUND OF THE INVENTION

Field of the Invention--.

005250-1428940

before line 4, insert

--Discussion of the Background--.

Page 2, before line 29, insert

--SUMMARY OF THE INVENTION--.

Page 5, before line 29, insert

--BRIEF DESCRIPTION OF THE DRAWINGS--.

Page 6, before line 1, insert

--DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS--.

IN THE CLAIMS

Page 14, change "CLAIMS" to

--WHAT IS NEW AND DESIRED TO BE SECURED BY LETTERS PATENT OF THE UNITED STATES IS--.

Please amend Claim 1-18 as follows:

1. (Amended) Process for manufacturing a composite tape [(10)] based on reinforcing fibres and on a thermoplastic organic material, consisting in bringing together and in consolidating a multiplicity of continuous yarns [(11)], characterized in that:

[-] yarns [(11)] based on thermoplastic and reinforcing fibres and entrained and brought together in a parallel manner in the form of a sheet [(12)];

[- the] said sheet [(12)] is made to enter a zone in which it is heated to a temperature reaching at least the melting point of the thermoplastic without reaching the softening temperature of the reinforcing fibres;

[-] the sheet [(12)] is made to pass through a rotating impregnation device [(80)], while maintaining its temperature at a temperature at which the thermoplastic is malleable, in order to distribute the molten thermoplastic uniformly and guarantee that the reinforcing

fibres are completely impregnated by the latter;

[-] the sheet [(12)] is introduced into a shaping and centring device [(100)], while maintaining its temperature at a temperature at which the thermoplastic is malleable, so as to obtain a tape [(13)] formed by bringing the yarns [(11)] together so as to be touching, thereby creating transverse continuity;

[-] the tape [(13)] is cooled in order to consolidate the yarns by freezing the thermoplastic and its dimensional characteristics and its appearance are set in order to deliver [the] said composite tape [(10)].

Claim 2, line 2, delete "(11)".

Claim 3, line 1, delete "or 2".

Claim 4, line 2, delete "(11)", and

line 3, delete "(12)".

Claim 5, line 2, delete "(12)", and

line 4, delete "(80)".

Claim 6, line 3, delete "(10)".

7. (Amended) Apparatus for implementing the process according to [any one of Claims] Claim 1 [to 6], characterized in that it comprises:

[-] means [(130)] for entraining the continuous yarns [(11)] consisting of reinforcing filaments and of thermoplastic filaments and means [(50)] for bringing [the] said continuous yarns into the form of a sheet [(12)];

[-] means [(70)] for heating [the] said sheet [(12)] to a temperature reaching at least the melting point of the thermoplastic but not the softening temperature of the reinforcing filaments;

[-] a rotating device [(80)] for impregnating the heated sheet so as to distribute the molten thermoplastic uniformly and guarantee that the reinforcing filaments are completely

impregnated by the latter;

[-] a device [(100)] for shaping and centring the sheet [(12)] so as to convert it into a tape [(13)];

[-] a calender [(110)] for cooling the tape [(13)], making it possible to freeze the thermoplastic and to consolidate the yarns [(11)] and form the final tape [(10)].

Claim 8, line 2, delete "(90)";

line 3, delete "(12)"; and

line 5, delete "(80)".

Claim 9, line 2, delete "(70, 90)".

Claim 10, line 2, delete "(50)";

line 3, delete "(51)"; and

line 4, delete "(11)".

Claim 11, line 2, delete "(80)";

line 3, delete "(81)"; and

line 5, delete "(12)".

Claim 12, line 2, delete "(81)"; and

same line, delete "(82)".

Claim 13, line 2, delete "(100)";

line 3, delete "(101)";

same line, delete "(102)";

line 6, delete "(12)"; and

line 8, delete "(13)".

Claim 14, line 2, delete "(110)";

line 4, delete "(13)"; and

line 6, delete "(10)".

Claim 15, line 2, delete "(110)";

line 3, delete "(120)"; and

line 4, delete "(10)".

Claim 16, line 2, delete "(40)";

line 3, delete "(11)"; and

same line, delete "(50)".

Claim 17, line 3, delete "(70)".

Claim 18, line 3, delete "(130)";

line 4, delete "(140)"; and

same line, delete "(10)".

IN THE ABSTRACT

Please delete the abstract in its entirety and insert the following new abstract:

--ABSTRACT OF THE DISCLOSURE

Process for manufacturing a composite tape including the steps of bringing together and consolidating a multiplicity of continuous yarns. The yarns are based on a thermoplastic and reinforcing fibres that are entrained and brought together in a parallel manner in the form of a sheet which enters a zone that is heated to a temperature reaching at least the melting point of the thermoplastic and then passes through a rotating impregnation device in order to distribute the molten thermoplastic uniformly and guarantee that the reinforcing fibres are completely impregnated by the latter. The sheet is then introduced into a shaping and centring device so as to obtain a tape formed by bringing the yarns together so as to be touching, thereby creating transverse continuity. The tape is cooled in order to consolidate the yarns by freezing the thermoplastic and its dimensional characteristics and its appearance are set in order to deliver the composite tape.--


REMARKS

Favorable reconsideration of this application as presently amended is respectfully requested.

Claims 1-19 are presently active in this case. Claims 1-18 having been amended by way of the Preliminary Amendment. A substitute Abstract of the Disclosure has also been provided in the present Preliminary Amendment. Therefore, a full and thorough examination on the merits of Claims 1-19 is requested.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Gregory J. Maier
Attorney of Record
Registration No. 25,599
Christopher D. Ward
Registration No. 41,367



22850

Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 11/98)

GJM:CDW:brf

I:\atty\cdw\1247\0849.Pre Amend.wpd



09/25/00 16:28:50

005250-1225950

The invention relates to the manufacture of a composite tape based on reinforcing fibres and on a thermoplastic organic material.

Composites based on a thermoplastic and on reinforcing fibres are widely used in the reinforcement of all types of articles, especially for the manufacture of composite pipes intended for conveying pressurized gases or liquids.

Patent Application FR 2,516,441 discloses a process for manufacturing thin sections comprising unidirectional continuous glass fibres embedded in a thermoplastic resin.

The steps of the process for obtaining such sections are as follows:

- 15 - unwinding glass yarns from reels, in order to form a sheet of yarns;
- separating the fibres of the yarns, in order to separate them because of the size with which they are coated;
- 20 - dipping the sheet of glass fibres into an aqueous bath of a thermoplastic or else in a fluidized bed of powder of a thermoplastic;
- heating the sheet in order to evaporate the water or to melt the powder, depending on the mode of dipping;
- 25 - hot shaping the resin-encapsulated sheet of fibres so as to produce the desired section.

One drawback with this process is that it is necessary, in order for the fibres to be uniformly impregnated with the thermoplastic, to introduce the step of separating the fibres. This requires a specific device using several rollers, the number and arrangement of which, for ensuring the suitable winding angle of the sheet on these rollers, are determined by the degree to which the fibres stick together.

In addition, it is sometimes necessary, when the degree of sticking is too high, to provide heating means complementary to the rollers.

Consequently, there is a possibility that all the fibres are not completely separated from each

other, in order subsequently to allow them to be encapsulated with the thermoplastic.

Moreover, the process uses for the impregnation a bath of thermoplastic which has to be maintained at a constant level the dispersion of which thermoplastic is constantly circulated in order to ensure as constant an impregnation as possible. Furthermore, the means employed in this bath are considerable and difficult to manage in a manufacturing line; these are elements such as a liquid delivery pump, a weir for establishing a constant level, a storage bath for the overflow, and a stirring device for ensuring that the contents of the bath are homogeneous, these elements having to be regularly cleaned.

In the variant of the impregnation device for the use of a fluidized bed, specific means are also necessary, especially a vibrating system mounted on springs, for metering the amount of powder taken away by the fibres.

Finally, the shaping device consists of a lower roller provided with a groove through which the sheet runs and of an upper roller serving to press the sheet. Thus, the various expected gauges of the section entail the drawback of having to have available several rollers which have variously sized grooves, respectively.

Consequently, this process, being slow to carry out, proves to be expensive and of low performance.

The object of the present invention is therefore to provide a process for manufacturing a composite based on reinforcing fibres and on a thermoplastic organic material, which process is easy and rapid to implement and is economic from an industrial standpoint.

More particularly, the invention provides, by virtue of this process, a product in the form of a strong flexible tape having a constant thickness of less than 0.2 mm and consisting of continuous reinforcing yarns arranged so as to be parallel and

005560.1423990

touching each other and consolidated by thermoplastic in order to create transverse continuity without any air being present, the tape having a smooth surface appearance and a void content of less than 0.2%.

5 According to the invention, the process for manufacturing the tape is characterized in that:

- yarns based on thermoplastic and reinforcing fibres are entrained and brought together in a parallel manner in the form of a sheet;
- 10 - the said sheet is made to enter a zone in which it is heated to a temperature reaching at least the melting point of the thermoplastic without reaching the softening temperature of the reinforcing fibres;
- 15 - the sheet is made to pass through a rotating impregnation device, while maintaining its temperature at a temperature at which the thermoplastic is malleable, in order to distribute the molten thermoplastic uniformly and guarantee that the reinforcing fibres are completely impregnated by the latter;
- 20 - the sheet is introduced into a shaping and centring device, while maintaining its temperature at a temperature at which the thermoplastic is malleable, so as to obtain a tape formed by bringing the yarns together so as to be touching, thereby creating transverse continuity;
- 25 - the tape is cooled in order to consolidate the yarns by freezing the thermoplastic and its dimensional characteristics and its appearance are set in order to deliver the said composite tape of the invention.
- 30

35 According to one characteristic, the yarns that are brought together consist of continuous glass filaments and continuous thermoplastic filaments which are co-mingled.

 According to another characteristic, the process consists in unreeling, from wound packages, a

0056821-002500

continuous yarn of reinforcing filaments and thermoplastic filaments and, while the yarns are being brought together in the form of a sheet, in regulating the tension in the yarns.

5 Advantageously, the yarns are stripped of any static electricity before the sheet passes into the heating zone.

According to another characteristic, the sheet is introduced into an additional heating zone after it has passed through the rotating impregnation device.

With regard to the apparatus for implementing the process, this is characterized in that it comprises:

- means for entraining the continuous yarns consisting of reinforcing filaments and of thermoplastic filaments and means for bringing the said continuous yarns into the form of a sheet;
- means for heating the said sheet to a temperature reaching at least the melting point of the thermoplastic but not the softening temperature of the reinforcing filaments;
- a rotating device for impregnating the heated sheet so as to distribute the molten thermoplastic uniformly and guarantee that the reinforcing filaments are completely impregnated by the latter;
- a device for shaping and centring the sheet so as to convert it into a tape;
- a calender for cooling the tape, making it possible to freeze the thermoplastic and to consolidate the yarns and form the final tape.

According to one characteristic, the apparatus comprises additional heating means so as to keep the thermoplastic of the sheet malleable after the latter 35 has passed through the impregnation device.

According to another characteristic, the means of the apparatus for bringing the yarns together

According to another characteristic, the impregnation device comprises three heated rotating rolls which are arranged in a triangular configuration and between which the sheet runs, the roll separation height being adapted in order to apply suitable pressure to the surface of the sheet.

According to another characteristic, the shaping and centring device comprises a lower roller and an upper roller which are offset, one above the other, and rotating in opposite directions, the upper roller being in the form of a hyperboloid, and the sheet being concentrated around the central running axis as it passes between the two rollers in order to deliver a tape constituting a mutually contiguous association of yarns.

Advantageously, the cooling calender of the apparatus consists of two rotating cooling rolls which are arranged one above the other and which do not have guiding edges, the calender thus giving the composite tape its final shape.

Preferably, the cooling calender includes, downstream of the rolls, a bath in which the running composite final tape is immersed.

Further features and advantages will now be
30 described with regard to the drawings in which:

- Figure 1 is a schematic side view of the apparatus for manufacturing a tape according to the invention;

- Figures 2 to 5 are perspective views of certain
35 parts of the apparatus in Figure 1, respectively of a
device for regulating the tension in the yarns, of the
rotating impregnation device, of the shaping and
centring device and of the cooling calender.

5

15

25

30

35

Consequently, it will be preferred to use an unreeling-type creel, especially for producing a small

tape thickness (of less than 0.2 mm). However, in this case it proves to be necessary to provide a regulating device, referenced 40 in Figures 1 and 2.

5 This device 40 makes it possible to adjust the overall level of tension in the sheet of yarns.

The eyeletted plate 30, which can also be seen in Figure 2, lies in a vertical plane parallel to the rotating spindles 21 of the creel. The eyeletted plate allows the yarns 11, each of which passes through an
10 eyelet 31 in order to be guided towards the tension-regulating device 40 at an angle appropriate to the desired tension, to be grouped together. The eyelets 31 are made, in a known manner, of a ceramic in order to prevent the yarns from being damaged as they pass
15 through them.

The tension-regulating device 40 which is illustrated in Figure 2 is combined with the eyeletted plate 30. It comprises a series of cylindrical bars 41 arranged in a staggered configuration one above
20 another, the yarns 11 coming from the eyeletted plate 30 travelling over and under these bars so as to define identical sinusoids, the amplitude of which influences the tension in the yarns. The height of the bars can be adjusted so as to be able to modify the amplitude of
25 the sinusoids, an increased amplitude imposing a higher tension in the yarns.

The bars are advantageously made of brass or of a ceramic in order to limit the static electricity phenomena induced by the rubbing of the yarns.

30 Placed at the exit of the device 40 is a comb 50 whose tines 51 group the yarns 11 together into a uniformly-spaced parallel alignment in order to obtain a sheet 12 in the form of bundles of yarns.

Installed between the comb 50 and the entrance
35 of the first oven 70 is an electrical device 60 serving to remove any static electricity with which the yarns 11 might be charged, so as to prevent the said yarns from bulking which, otherwise, would cause them to degrade in the oven 70.

005220-1633520

The first oven 70 and likewise the second oven 90 operate by a convection of hot air. They could just as well be infrared ovens.

By passing through the first oven 70, the sheet 5 12 is heated to a temperature such that on leaving the oven the sheet has a temperature high enough to reach the melting point of the thermoplastic of the yarns 11 so that the molten thermoplastic sticks together and is embedded in the glass filaments of the entire sheet 12.

10 Between and outside the ovens 70 and 90 there
is a rotating impregnation device 80 which flattens the
sheet 12 so as to expel the air contained between the
yarns, distribute the molten thermoplastic uniformly
over the width of the sheet and guarantee that the
15 glass filaments are completely impregnated by the
thermoplastic.

The rotating impregnation device 80, which can be seen in Figure 3, consists of three mutually parallel rolls 81 arranged in a triangular 20 configuration so as to have two lower rolls and one upper roll. The rolls are heated and reach a temperature high enough to maintain the thermoplastic of the sheet in a malleable state.

The rolls 81 rotate, the lower ones rotating in
25 the positive direction with respect to the running
direction F of the sheet 12 while the upper one rotates
in the opposite direction, the rotation speeds being
identical and corresponding to that at which the sheet
runs.

30 The height of the upper roll can be adjusted in order to apply pressure to the sheet 12 high enough to ensure that the glass is impregnated by the thermoplastic.

Since the rolls 81 are in contact with the
35 sheet, a film of thermoplastic is rapidly deposited
onto their surfaces. Advantageously, the said rolls
each have a blade 82 whose action is to scrape their
surfaces and whose purpose is at the same time to
prevent the formation of any spurious winding of the

glass filaments and to help in achieving homogeneous distribution of the molten thermoplastic along the length of the tape. Thus, should there be an excessively thick film on each roll, this excess is
5 used to supplement the encapsulation of the glass filaments which might be insufficiently coated.

The inclination of the blades 82 can be adjusted so as to optimize their effectiveness.

As a variant, for the same purpose of
10 regulating the distribution of thermoplastic, instead of using the blades 82 the three rolls are driven at a slightly lower speed of rotation than the speed at which the sheet runs. This solution means that not only do the rolls 82 have to be driven but also that a speed
15 control mechanism has to be installed.

The temperature setting of the second oven 90 is such that the thermoplastic of the running sheet remains malleable.

Note that it would be conceivable to use a
20 single oven in which the impregnation device 80 would be housed, the impregnation device being able to withstand the temperature of the oven.

Placed at the exit of the second oven is a shaping and centring device 100 which, as illustrated
25 in Figure 4, comprises a cylindrical lower roller 101 and a hyperboloidal upper roller 102 which is slightly offset upstream with respect to the vertical through the lower roller, both rollers rotating and being heated in order to maintain the temperature at which
30 the thermoplastic of the sheet 12 is malleable.

The purpose of the device 100 is to convert the sheet 12 into a tape 13 of constant thickness formed by bringing the yarns 11 together so as to be touching, in order to create transverse continuity in the said tape.
35 Thus, the device 100 concentrates the sheet around the central axis of the line in order to reduce its width, which had been increased during its passage through the impregnation device 80, and recentres the sheet with respect to the central axis of the manufacturing line

00558241-102500

in order to suitably guide the tape downstream towards the calender 110.

The gathering and guiding towards the centre is achieved by the hyperboloidal shape of the upper roller 102 which, by adjusting its height, also allows light pressure to be applied to the upper surface of the sheet in order to concentrate it.

The counter rotation of the rollers 101 and 102 firstly prevents the thermoplastic from drying and secondly prevents it from accumulating, which could impair the uniformity of its distribution and consequently the thickness of the tape.

A calender 110, which can be seen in Figure 5, is located downstream of the device 100 for the purpose of giving the tape 13 its final dimensional characteristics and its final appearance, so as to have a finished tape 10. The calender 110 adjusts the final thickness of the tape and at the same time cools it in order to freeze the thermoplastic, giving it a smooth surface appearance.

The calender consists of two counter rotating rolls 111 arranged one above the other and made to rotate by the tape running through them.

The two rolls 111 are cooled by internal circulation of water so as to freeze the thermoplastic and consolidate the yarns.

The thickness of the tape 10 is accurately controlled by the gap set between the two rolls using adjustable stops 112. A pneumatic cylinder 113 provides the pressure to be applied to the surface of the tape in order to even out all the thickness variants that might occur. It thus fulfils the role of locking the position of the adjustable stops 112.

It should be emphasized that the calender 110 does not have any guiding edges which, in the known calendering devices, make it possible to impose a width on the element to be calendered. This is because, in the invention, the width is defined by the number of

yarns 11 used for manufacturing the tape. The absence of edges has the advantage of not shearing the yarns.

The final cooling of the tape is achieved by means of the water bath 120, placed after the calender 110, and in which the running tape 10 is immersed.

Installed beyond this bath is a caterpillar haul-off 130 which constitutes, in a known manner, a means of entraining the yarns and the tape, by exerting a tensile force all along the line. It sets the pay-out speed and the run speed of the sheet and then of the tape.

Finally, the manufacturing apparatus 1 may include, at the end of the line, a winder 140 intended to wind the tape in order to form a reel, so as to make it easier to store it.

The process for manufacturing the tape according to the invention will now be described. The example given below produces a glass/polyethylene composite tape with a width of 90 mm and a thickness of 0.2 mm, its void content being less than 0.2%.

The start-up of the process begins by manually pulling each yarn 11 off the packages 2 and manually taking it as far as the haul-off 130 where each yarn is then held clamped, all the yarns passing through the various devices described above. In this example of application, there are 28 rovings of glass/polyethylene co-mingled composite yarn having the trademark Twintex®, the 982 tex overall linear density of which comprises 60% glass by weight.

30 The ovens 70 and 90 as well as the heating
elements of the apparatus 1 are raised in temperature
so as to reach the following temperatures:

- ```

- oven 70: 370°C;
- oven 90: 280°C;
35 - rotating rolls of the impregnation device 80:
290°C;
- rollers of the shaping and centring device 100:
270°C.

```

The haul-off 130 is switched on and payout from the packages 2 starts.

The yarns 11 pass through the eyelets 31, then astride the bars in the device 40 and are brought  
5 together through the tines of the comb 50 in order to form, at the exit, the sheet 12 of parallel yarns.

The sheet 12 then meets the device 60 which removes any static electricity.

Next, the sheet enters the first oven 70 so that the thermoplastic reaches its melting point. Thereafter, it passes between the heated rolls of the device 80 which make it possible for it to be rolled, expelling the air, and to uniformly distribute the thermoplastic which thus encapsulates the glass  
15 filaments. We should point out that the amount of thermoplastic does not have to be metered since it is directly incorporated into the raw material of the tape by it being co-mingled with the glass filaments. The temperature of the sheet, after it has passed through  
20 this device 80, reaches 190°C.

The sheet 12 then passes through the second oven 90 in order to maintain the thermoplastic in a malleable state so that, on leaving the oven, it runs between the rollers 102 of the shaping and centring  
25 device 100, in order to convert it into a tape 13 which is shaped by closing up the yarns against each other and placing them so that they touch each other. After shaping, the tape has a temperature of 210°C.

Next, the tape 13 passes between the rolls 111  
30 of the cold calender 110 in order to give it its final shape, by freezing the thermoplastic and consolidating the yarns. The tape 10 of the invention is obtained with a constant thickness and a smooth appearance. The tape has a temperature of 100°C on leaving the  
35 calender.

In order to facilitate and speed up the cooling of the entire tape 10, the latter is immersed in a water bath 120 and becomes, on leaving it, its temperature being 30°C, a strong product sufficiently

00562941-0042500

flexible to be wound up by means of a winder 140 in the form of a reel, for ease of storage, transportation and use.

005250-16289360

**CLAIMS**

1. Process for manufacturing a composite tape  
(10) based on reinforcing fibres and on a thermoplastic  
5 organic material, consisting in bringing together and  
in consolidating a multiplicity of continuous yarns  
(11), **characterized in that:**

- yarns (11) based on thermoplastic and reinforcing fibres are entrained and brought together in a parallel manner in the form of a sheet (12);
- the said sheet (12) is made to enter a zone in which it is heated to a temperature reaching at least the melting point of the thermoplastic without reaching the softening temperature of the reinforcing fibres;
- the sheet (12) is made to pass through a rotating impregnation device (80), while maintaining its temperature at a temperature at which the thermoplastic is malleable, in order to distribute the molten thermoplastic uniformly and guarantee that the reinforcing fibres are completely impregnated by the latter;
- the sheet (12) is introduced into a shaping and centring device (100), while maintaining its temperature at a temperature at which the thermoplastic is malleable, so as to obtain a tape (13) formed by bringing the yarns (11) together so as to be touching, thereby creating transverse continuity;
- the tape (13) is cooled in order to consolidate the yarns by freezing the thermoplastic and its dimensional characteristics and its appearance are set in order to deliver the said composite tape (10).

2. Process according to Claim 1, **characterized in that** the yarns (11) that are brought together

3. Process according to Claim 1 or 2, **characterized in that** it consists in unreeling, from wound packages, a continuous yarn of reinforcing filaments and thermoplastic filaments and, while the yarns are being brought together in the form of a sheet, in regulating the tension in the yarns.

4. Process according to claim 1, **characterized in that** the yarns (11) are stripped of any static electricity before the sheet (12) passes into the heating zone.

5. Process according to Claim 1, **characterized in that** the sheet (12) is introduced into an additional heating zone after it has passed through the rotating impregnation device (80).

6. Process according to Claim 1, **characterized in that**, at the end of the manufacturing line, the tape (10) is wound up in the form of a reel for storing it.

7. Apparatus for implementing the process according to any one of Claims 1 to 6, **characterized in that** it comprises:

- means (130) for entraining the continuous yarns (11) consisting of reinforcing filaments and of thermoplastic filaments and means (50) for bringing the said continuous yarns into the form of a sheet (12);
- means (70) for heating the said sheet (12) to a temperature reaching at least the melting point of the thermoplastic but not the softening temperature of the reinforcing filaments;
- a rotating device (80) for impregnating the heated sheet so as to distribute the molten thermoplastic uniformly and guarantee that the reinforcing filaments are completely impregnated by the latter;
- a device (100) for shaping and centring the sheet (12) so as to convert it into a tape (13);

- a calender (110) for cooling the tape (13), making it possible to freeze the thermoplastic and to consolidate the yarns (11) and form the final tape (10).

- 5           8. Apparatus according to Claim 7, **characterized in that** it comprises additional heating means (90) so as to keep the thermoplastic of the sheet (12) malleable after the latter has passed through the impregnation device (80).
- 10          9. Apparatus according to Claim 8, **characterized in that** the two heating means (70, 90) are ovens.
10. Apparatus according to Claim 7, **characterized in that** the means (50) for bringing the yarns together consist of a comb, the tines (51) of which produce a
- 15          uniformly-spaced parallel alignment of the yarns (11).
11. Apparatus according to Claim 7, **characterized in that** the impregnation device (80) comprises three heated rotating rolls (81) which are arranged in a triangular configuration and between which the sheet
- 20          (12) runs, the roll separation height being adapted in order to apply suitable pressure to the surface of the sheet.
12. Apparatus according to Claim 11, **characterized in that** each roll (81) has a blade (82)
- 25          for scraping off the molten thermoplastic deposited on the roll after the sheet has passed.
13. Apparatus according to Claim 7, **characterized in that** the shaping and centring device (100) comprises a lower roller (101) and an upper roller (102) which
- 30          are offset, one above the other, and rotating in opposite directions, the upper roller being in the form of a hyperboloid, and the sheet (12) being concentrated around the central running axis as it passes between the two rollers in order to deliver a tape (13)
- 35          constituting a mutually contiguous association of yarns.
14. Apparatus according to Claim 7, **characterized in that** the cooling calender (110) consists of two rotating cooling rolls which are arranged one above the

00660001-092500



other and between which the tape (13) runs and which do not have guiding edges, the calender giving the composite tape (10) its final shape.

15       15. Apparatus according to Claim 14, **characterized in that** the cooling calender (110) includes, downstream of the rolls, a bath (120) in which the running composite final tape (10) is immersed.

10       16. Apparatus according to Claim 7, **characterized in that** means (40) for regulating the tension in the yarns (11) are provided upstream of the means (50) for bringing the yarns together.

15       17. Apparatus according to Claim 7, **characterized in that** an antistatic device is provided upstream of the heating means (70).

20       18. Apparatus according to Claim 7, **characterized in that** it includes, at the end of the manufacturing line and downstream of the entrainment means (130), a winder (140) allowing the tape (10) to be wound in the form of a reel.

25       19. Tape obtained according to the process of Claim 1, **characterized in that** it constitutes a strong flexible product of smooth surface appearance, having a thickness of less than 0.2 mm and a void content of less than 0.2%.

005260-1623960

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176

# 2025 RELEASE UNDER E.O. 14176



FIG. 1

FIG 2





FIG 3

005260-16289960




FIG. 4




FIG. 5

NA 4 990 59 US

# Declaration and Power of Attorney for Patent Application

## Déclaration et Pouvoirs pour Demande de Brevet

### French Language Declaration

En tant l'inventeur nommé ci-après, je déclare par le présent acte que

As a below named inventor, I hereby declare that:

Mon domicile, mon adresse postale et ma nationalité sont ceux figurant ci-dessous à côté de mon nom

My residence, post office address and citizenship are as stated next to my name.

Je crois être le premier inventeur original et unique (si un seul nom est mentionné ci-dessous), ou l'un des premiers co-inventeurs originaux (si plusieurs noms sont mentionnés ci-dessous) de l'objet revendiqué, pour lequel une demande de brevet a été déposée concernant l'invention intitulée

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

\_\_\_\_\_

\_\_\_\_\_

\_\_\_\_\_

PROCESS FOR MANUFACTURING A COMPOSITE

TAPE FORMED FROM REINFORCING FIBRES AND

FIBRES OF A THERMOPLASTIC ORGANIC  
MATERIAL

et dont la description est fournie ci-joint à moins

the specification of which

☐ ci-joint

☒ is attached hereto.

☐ a été déposée le \_\_\_\_\_

☐ was filed on \_\_\_\_\_

sous le numéro de demande des Etats-Unis ou le  
numéro de demande international PCT

**Atty. Docket No. 1247-0849-6VF**  
as United States Application Number or PCT  
International Application Number

\_\_\_\_\_ et modifiée le

\_\_\_\_\_ and was amended on

\_\_\_\_\_ (le cas échéant)

**even date by Preliminary Amendment**  
(if applicable).

Je déclare par le présent acte avoir passé en revue et compris le contenu de la description ci-dessus, revendications comprises, telles que modifiées par toute modification dont il aura été fait référence ci-dessus.

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

Je reconnais devoir divulguer toute information pertinente à la brevetabilité, comme défini dans le Titre 37, § 1.56 du Code fédéral des réglementations.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

## French Language Declaration

Je revendique par le présent acte avoir la priorité étrangère, en vertu du Titre 35, § 119(a)-(d) ou § 365(b) du Code des Etats-Unis, sur toute demande étrangère de brevet ou certificat d'inventeur ou, en vertu du Titre 35, § 365(a) du même Code, sur toute demande internationale PCT désignant au moins un pays autre que les Etats-Unis et figurant ci-dessous et, en cochant la case, j'ai aussi indiqué ci-dessous toute demande étrangère de brevet, tout certificat d'inventeur ou toute demande internationale PCT ayant une date de dépôt précédant celle de la demande à propos de laquelle une priorité est revendiquée

Prior Foreign Application(s)  
Demande(s) de brevet antérieure(s) dans un autre pays

99/13067 FRANCE  
(Number) (Country)  
(Numéro) (Pays)

(Number) (Country)  
(Numéro) (Pays)

I hereby claim foreign priority under Title 35, United States Code, § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below, and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority claimed  
Droit de priorité  
revendiquée

20/OCTOBER/1999 ☒ ☐  
(Day/Month/Year Filed) Yes No  
(Jour/Mois/Année de dépôt) Oui Non

(Day/Month/Year Filed) ☐ ☐  
(Jour/Mois/Année de dépôt) Yes No  
Oui Non

Je revendique par le présent acte tout bénéfice, en vertu du Titre 35, § 119(e) du Code des Etats-Unis, de toute demande de brevet provisoire effectuée aux Etats-Unis et figurant ci-dessous

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below.

(Application No.) (Filing Date)  
(N° de demande) (Date de dépôt)

(Application No.) (Filing Date)  
(N° de demande) (Date de dépôt)

Je revendique par le présent acte tout bénéfice, en vertu du Titre 35, § 120 du Code des Etats-Unis, de toute demande de brevet effectuée aux Etats-Unis, ou en vertu du Titre 35, § 365(c) du même Code, de toute demande internationale PCT désignant les Etats-Unis et figurant ci-dessous et, dans la mesure où l'objet de chacune des revendications de cette demande de brevet n'est pas divulgué dans la demande antérieure américaine ou internationale PCT, en vertu des dispositions du premier paragraphe du Titre 35, § 112 du Code des Etats-Unis, je reconnais devoir divulguer toute information pertinente à la brevetabilité, comme défini dans le Titre 37, § 156 du Code fédéral des réglementations, dont j'ai pu disposer entre la date de dépôt de la demande antérieure et la date de dépôt de la demande nationale ou internationale PCT de la présente demande

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 156 which became available between the filing date of the prior application and the national or PCT International filing date of this application

(Application No.) (Filing Date)  
(N° de demande) (Date de dépôt)

(Status) (patented, pending, abandoned)  
(Statut) (breveté, en cours d'examen, abandonné)

(Application No.) (Filing Date)  
(N° de demande) (Date de dépôt)

(Status) (patented, pending, abandoned)  
(Statut) (breveté, en cours d'examen, abandonné)

Je déclare par le présent acte que toute déclaration ci-incluse est, à ma connaissance, véridique et que toute déclaration formulée à partir de renseignements ou de suppositions est tenue pour véridique, et de plus, que toutes ces déclarations ont été formulées en sachant que toute fausse déclaration volontaire ou son équivalent est passible d'une amende ou d'une incarcération, ou des deux, en vertu de la Section 1001 du Titre 18 du Code des Etats-Unis, et que de telles déclarations volontairement fausses risquent de compromettre la validité de la demande de brevet ou du brevet délivré à partir de celle-ci.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

## French Language Declaration

POUVOIRS. En tant que l'inventeur cité, je désigne par la présente l'(ies) avocat(s) et/ou agent(s) suivant(s) pour qu'il(s) poursuive(nt) la procédure de cette demande de brevet et traite(nt) toute affaire s'y rapportant avec l'Office des brevets et des marques (mentionner le nom et le numéro d'enregistrement).

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

Norman F. Oblon, Reg. No. 24,618; Marvin J. Spivak, Reg. No. 24,913; C. Irvin McClelland, Reg. No. 21,124; Gregory J. Maier, Reg. No. 25,599; Arthur I. Neustadt, Reg. No. 24,854; Richard D. Kelly, Reg. No. 27,757; James D. Hamilton, Reg. No. 28,421; Eckhard H. Kuesters, Reg. No. 28,870; Robert T. Pous, Reg. No. 29,099; Charles L. Gholz, Reg. No. 26,395; William E. Beaumont, Reg. No. 30,996; Robert F. Gnuse, Reg. No. 27,295; Jean-Paul Lavallée, Reg. No. 31,451; Stephen G. Baxter, Reg. No. 32,884; Robert W. Hahl, Reg. No. 33,893; Richard L. Treanor, Reg. No. 36,379; Steven P. Wehrhouch, Reg. No. 32,829; John T. Goolkasian, Reg. No. 26,142; Richard L. Chinn, Reg. No. 34,305; Steven E. Lipman, Reg. No. 30,011; Carl E. Schlier, Reg. No. 34,426; James J. Kulbaski, Reg. No. 34,648; Richard A. Neifeld, Reg. No. 35,299; J. Derek Mason, Reg. No. 35,270; Surinder Sachar, Reg. No. 34,423; Christina M. Gadano, Reg. No. 37,628; Jeffrey B. McIntyre, Reg. No. 36,867; Paul E. Rauch, Reg. No. 38,591; William T. Enos, Reg. No. 33,128 and Michael E. McCabe, Jr., Reg. No. 37,182, with full powers of substitution and revocation.

Addresser toute correspondance à:

Send Correspondence to:

OBLON, SPIVAK, MCCLELLAND, MAIER & NEUSTADT, P.C.

FOURTH FLOOR  
1755 JEFFERSON DAVIS HIGHWAY  
ARLINGTON, VIRGINIA 22202 U S A

Addresser tout appel téléphonique à  
(nom et numéro de téléphone)

Direct Telephone calls to: (name and telephone number)

(703) 413-3000

|                                                     |                                                                          |
|-----------------------------------------------------|--------------------------------------------------------------------------|
| Nom complète de l'unique ou premier inventeur       | Full name of sole or first inventor                                      |
| Signature de l'inventeur                            | <u>Jean-Paul DEBATME</u><br>Inventor's signature                         |
| Date                                                | Date<br>07.28.2000                                                       |
| Domicile                                            | Residence <u>10, boulevard de Lemenc</u><br><u>73000 CHAMBERY FRANCE</u> |
| Nationalité                                         | Citizenship<br><u>FRANCE</u>                                             |
| Adresse Postale                                     | Post Office Address<br><u>Same as above</u>                              |
|                                                     |                                                                          |
| Nom complète du second co-inventeur, le cas échéant | Full name of second joint inventor, if any                               |
| Signature de l'inventeur                            | <u>Jacques VOIRON</u><br>Second inventor's signature                     |
| Date                                                | Date<br>07.31.2000                                                       |
| Domicile                                            | Residence <u>Cote Barrier</u><br><u>73160 ST JEAN DE OUZE FRANCE</u>     |
| Nationalité                                         | Citizenship<br><u>FRANCE</u>                                             |
| Adresse Postale                                     | Post Office Address<br><u>Same as above</u>                              |
|                                                     |                                                                          |

(Fournir les mêmes renseignements et la signature de tout co-inventeur supplémentaire)

(Supply similar information and signature for third and subsequent joint inventors)



## French Language Declaration

|                                                                  |                                                                           |
|------------------------------------------------------------------|---------------------------------------------------------------------------|
| Nom complet du troisième co-inventeur, le cas échéant            | Full name of third joint inventor, if any<br>Alexandre CIVIDINO           |
| Signature de l'inventeur <span style="float: right;">Date</span> | Third Inventor's signature <span style="float: right;">Date</span>        |
| Domicile                                                         | Residence <i>08.07.2000</i><br>9, Rue Docteur Desfrancois - Appartement 6 |
| Nationalité                                                      | Citizenship 73000 CHAMBERY FRANCE                                         |
| Adresse Postale                                                  | Post Office Address<br>Same as above                                      |
|                                                                  |                                                                           |

|                                                                  |                                                                     |
|------------------------------------------------------------------|---------------------------------------------------------------------|
| Nom complet du quatrième co-inventeur, le cas échéant            | Full name of fourth joint inventor, if any                          |
| Signature de l'inventeur <span style="float: right;">Date</span> | Fourth Inventor's signature <span style="float: right;">Date</span> |
| Domicile                                                         | Residence                                                           |
| Nationalité                                                      | Citizenship                                                         |
| Adresse Postale                                                  | Post Office Address                                                 |
|                                                                  |                                                                     |

|                                                                  |                                                                    |
|------------------------------------------------------------------|--------------------------------------------------------------------|
| Nom complet du cinquième co-inventeur, le cas échéant            | Full name of fifth joint inventor, if any                          |
| Signature de l'inventeur <span style="float: right;">Date</span> | Fifth Inventor's signature <span style="float: right;">Date</span> |
| Domicile                                                         | Residence                                                          |
| Nationalité                                                      | Citizenship                                                        |
| Adresse Postale                                                  | Post Office Address                                                |
|                                                                  |                                                                    |

|                                                                  |                                                                    |
|------------------------------------------------------------------|--------------------------------------------------------------------|
| Nom complet du sixième co-inventeur, le cas échéant              | Full name of sixth joint inventor, if any                          |
| Signature de l'inventeur <span style="float: right;">Date</span> | Sixth Inventor's signature <span style="float: right;">Date</span> |
| Domicile                                                         | Residence                                                          |
| Nationalité                                                      | Citizenship                                                        |
| Adresse Postale                                                  | Post Office Address                                                |
|                                                                  |                                                                    |

(Fournir les mêmes renseignements et la signature de tout co-inventeur supplémentaire.)

(Supply similar information and signature for third and subsequent joint inventors.)